

Datasheet

_____ Blenheim Red Multi Wirecut Facing Brick

DETAILS FROM DOP



Brick type / Category	U / 1			
Intended use	Bricks for use in unprotected masonry			
Geometry	G1	In accordance with EN1996-1-1.		
Dimensions, [mm]	UK-NF	Length 215	Width 103	Height 65
Tolerance, [mm]	T2	Length ±4	Width ±3	Height ±2
Range, [mm]	Rm	Length 8	Width 6	Height 4
Gross density	1800	kg / m ³		
Tolerance	D1	±10%		
Compressive strength, average, min	25	N/mm ²		
Compressive strength, normalized, min	20	N/mm ²		
Water absorption, maximum	8	Weight%		
Durability against freeze/thaw	F2	Freeze/thaw resistant		
Active soluble salts content (Category)	S2			
Fire resistance	A1	contains < 1,0% organic material		
SUPPLEMENTAL INFORMATION				
Initial rate of absorption, average value ± tolerance	2,0 ± 0,5	kg/m ²		
Exposure class	MX4			
Bond strength	0,15	N/mm ² , table value, EN 998-2, annex C		
Bricks per m2 with a 10mm mortar joint	59	pcs / m ²		
Palletising	84	pcs		
Cleaning	Acid cleaning not recommended. See instructions for cleaning of masonry at randerstegl.com			
Mortar selection	The type of mortar is chosen on the basis of characteristics of strength and durability in accordance with static impacts and exposureclass.			
Note	Brick is a natural material and variations can thus occur in terms of colour and structure. Therefore please see samples or reference buildings with the brick products in question.			